Low Hardness Products 200 Series



TYPICAL PROPERTY DATA

Item	Standard(GB/T)	200	201	12K
Appearance	/	Transparent		Translucent
Curing agent	/	C-15		C-8
Phr (%)	/	2.0		2.0
Curing conditions	/	170℃×10min		170℃×5min
Hardness (Shore A)		8±2	25±2	20±2
Density (g/cm3)		0.08-1.04	1.05-1.09	1.06-1.10
Tensile Strength(MPa) ≥		0.7	5.5	3.0
Elongation (%) >		100	700	700
Tensile set (%)≤		6.0	10.0	10.0
Tear strength(KN/m) ≥		4.0	12.0	8.0

We reserve the right to alter product data within the scope of technical progress or new developments without notice.

Low Hardness Products 200 Series

HANDLING, SAFETY AND STORAGE

- Wear eye protection and protective glove when handling with this product.
- Store in a cool and dry place out of direct sunlight.
- Keep out of the reach of the children.

PACKAGING

♦ 20kg box with plastic bag inside

FOR INDUSTRIAL USE ONLY NEVER USE ANY SILICONES PRODUCT FOR IMPLANTATION OR INJECTION INTO THE HUMAN BODY.